

ISBN 978-0-626-21499-9

SANS 11427:1993

Edition 1 and ISO tech. corr. 1, nat. amdt 1

ISO 11427:1993

Edition 1 and tech. corr. 1

Any reference to SABS ISO 11427 is deemed
to be a reference to this standard
(Government Notice No. 1373 of 8 November 2002)

SOUTH AFRICAN NATIONAL STANDARD

Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using potassium bromide

This national standard is the identical implementation of ISO 11427:1993 and ISO technical corrigendum 1, and is adopted with the permission of the International Organization for Standardization.

Published by Standards South Africa
1 dr lategan road groenkloof ☒ private bag x191 pretoria 0001
tel: 012 428 7911 fax: 012 344 1568 international code + 27 12
www.stansa.co.za
© Standards South Africa

standards
SouthAfrica
(a division of SABS)

SANS 11427:1993

Edition 1 and ISO tech. corr. 1, nat. amdt 1

ISO 11427:1993

Edition 1 and tech. corr. 1

Table of changes

Change No.	Date	Scope
ISO tech. corr. 1	1994	Corrected to modify a requirement for potassium bromide solution.
Nat. amdt 1	2008	Amended to change the designation from SABS to SANS, with no technical changes.

National foreword

This South African standard was approved by National Committee StanSA TC 5120.78, *Engineering materials – Non-ferrous metals*, in accordance with procedures of Standards South Africa, in compliance with annex 3 of the WTO/TBT agreement.

This SANS document was published in August 2008. This SANS document supersedes SABS ISO 11427:1993 (edition 1).



Published 1994-11-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using potassium bromide

TECHNICAL CORRIGENDUM 1

Dosage de l'argent dans les alliages d'argent pour la bijouterie-joaillerie — Méthode volumétrique (potentiométrique) utilisant le bromure de potassium

RECTIFICATIF TECHNIQUE 1

Technical corrigendum 1 to International Standard ISO 11427:1993 was prepared by Technical Committee ISO/TC 174, *Jewellery*.

Page 1

Subclause 4.2

Replace 1 mol/l by 0,1 mol/l.

This page intentionally left blank

INTERNATIONAL STANDARD

ISO
11427

First edition
1993-05-01

Determination of silver in silver jewellery alloys — Volumetric (potentiometric) method using potassium bromide

*Dosage de l'argent dans les alliages d'argent pour la
bijouterie-joaillerie — Méthode volumétrique (potentiométrique) utilisant
le bromure de potassium*



Reference number
ISO 11427:1993(E)